







DESCRIPTION

Advantage+ 2K MS Clearcoat is an acrylic clearcoat with medium solids content. **Advantage+ 2K MS Clearcoat** can be used over solvent basecoats. It is easy to apply, fast drying and has a good gloss level.

Composition:	Acrylic Resins
Colour:	Clear
Shelf life:	36 months in unopened container
Pack size:	1 Litre/5 Litre
Pre-treatment:	FL2010 Advantage+ 2K MS Clearcoat can be applied over solvent basecoats.

	Health and safety "For professional use only" Important: When using any new product, consult the "Health and Safety" data sheet. Always read the risks and precautions stated on the product label.									
	Mixing Ratio 2 : 1 2 FL2010 Advantage+ 2K MS CLEARCOAT	1 FL2013 Advantage+ 2K MS HARDENER (Standard, Fast or Extra Fast)								
	Spraying Viscosity 17 to 20 seconds DIN4 cup 20°C Pot life - 8 hours at 20°C dependent on hardener speed combinations									
	1.2 – 1.4mm Nozzle/Tip Recommended Spray Pressure 2 bar at the gun									
	Number of coats 2 Apply 2 normal coats with a flash off time between coats of 3-5 minutes at 20°C.									
	Air Drying: at 20°C the film is dry after 30 minutes, may be handles with are after 90 minutes and may be re-coated after 8 hours after drying overnight (8 hours). Bake: <table border="1" style="margin-top: 5px;"> <thead> <tr> <th>Hardener</th> <th>Bake Time (65 °C Air Temp.)</th> </tr> </thead> <tbody> <tr> <td>Standard</td> <td>25 minutes</td> </tr> <tr> <td>Fast</td> <td>20 minutes</td> </tr> <tr> <td>Extra Fast</td> <td>15 minutes</td> </tr> </tbody> </table> Infra-Red: 10-15 minutes using conventional infrared.		Hardener	Bake Time (65 °C Air Temp.)	Standard	25 minutes	Fast	20 minutes	Extra Fast	15 minutes
Hardener	Bake Time (65 °C Air Temp.)									
Standard	25 minutes									
Fast	20 minutes									
Extra Fast	15 minutes									

Reworking: After cooling following the above stoving schedules, defects and runs can be removed using P1200 Wet or Dry. The paint surface can then be polished using a fine polishing paste or an ammonia-free compound.

Storage: Unmixed, correctly stored material, in firmly closed original container, has a shelf life of over a year. Contents of opened containers should be used up quickly. Always replace hardener caps immediately. Hardener mixtures cannot be stored.

The technical data contained herein is based on our present knowledge and we experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.